

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶: C09J 167/04	A1	(11) International Publication Number: WO 95/02649 (43) International Publication Date: 26 January 1995 (26.01.95)
(21) International Application Number: PCT/GB94/01496 (22) International Filing Date: 11 July 1994 (11.07.94) (30) Priority Data: 9314577.9 14 July 1993 (14.07.93) GB (71) Applicant (for all designated States except US): ZENECA LIMITED [GB/GB]; 15 Stanhope Gate, London W1Y 6LN (GB). (72) Inventor; and (75) Inventor/Applicant (for US only): KEMMISH, David, John [GB/GB]; 96 Dowber Way, Thirsk YO7 1EP (GB). (74) Agent: LOCKE, Timothy, John; Zeneca Bioproducts, Intellectual Property Group, P.O. Box 2, Belasis Avenue, Billingham, TS23 1YN (GB).		(81) Designated States: AT, AU, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, ES, FI, GB, GE, HU, JP, KE, KG, KP, KR, KZ, LK, LT, LU, LV, MD, MG, MN, MW, NL, NO, NZ, PL, PT, RO, RU, SD, SE, SI, SK, TJ, TT, UA, US, UZ, VN, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG), ARIPO patent (KE, MW, SD). Published <i>With international search report.</i>
(54) Title: ADHESION PROCESS (57) Abstract A process of bonding two or more articles together using an adhesive composition comprising at least one polyhydroxyalkanoate (PHA) wherein the PHA is placed between the articles to be bonded and the articles are subjected to pressure to set the adhesive, optionally at elevated temperatures.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

ADHESION PROCESS

THIS INVENTION relates to an adhesion process. More particularly it relates to a process of bonding articles together with an adhesive comprising a biodegradable polymer.

It is known to coat paper with polyhydroxyalkanoic acids (PHA), for example polymers of hydroxybutyric acid (PHB) and copolymers with hydroxyvaleric acid (PHBV) both as latex and as dry solid, preferably as dry powder. The coating is biodegradable but is non-adhesive.

We have now found that articles may be stuck together using PHA as an adhesive under cold application conditions and setting it with both articles in contact with one another under pressure and preferably with heat. The adhesive is biodegradable. The adhesive is believed to set by crystallisation.

Thus, according to the present invention there is provided a process of bonding two or more articles together using an adhesive composition comprising at least one polyhydroxyalkanoate (PHA) wherein the PHA is placed between the articles to be bonded and the articles are subjected to pressure to set the adhesive, optionally at elevated temperature.

The PHA is especially one capable of a relatively high level of crystallinity, for example over 30%, especially 50-90%, in the absence of plasticiser. Suitably it is or includes at least one microbiologically produced polyester having units of formula I:



where m is in the range 1-13 and n is 2m or (if m is at least 2) 2m-2. Typically $C_m H_n$ contains 2-5 carbon atoms

in the polymer chain and the remainder (if any) in a side chain. In very suitable polyesters n is $2m$ and there are preferably units with $m = 3$ and $m = 4$ copolymerised together and with respectively a C_1 and C_2 side chain on the carbon next to oxygen in the chain. The polymer may be homopolymer, especially a polyhydroxybutyrate (PHB), or a copolymer, especially a copolymer of hydroxybutyric acid and hydroxyvaleric acid (HV) containing preferably 4-30 mol% of $m=4$ units. Thus, particular polyesters contain a preponderance of $m = 3$ units, especially with 70 - 98 mol % of such units, the balance (if any) being units in which $m = 4$. The molecular weight of the PHA is preferably over 50000, especially over 100000, up to eg 2×10^6 .

The PHA may be a blend of two or more copolymers differing in the value of m . A particular example contains

- (a) PHA consisting essentially of Formula I units in which 2-5 mol % of units have $m = 4$, the rest $m = 3$; and
- (b) PHA consisting essentially of Formula I units in which 5-30 mol% of units have $m = 4$, the rest $m = 3$.

In each such PHA there are preferably side chains as above mentioned. The proportions in such a blend are preferably such as give an average $m = 4$ content in the range 4 - 30, more preferably 10-28, mol %.

In each such PHA having units with $m = 3$ and $m = 4$ there may be very small, typically fractional, percentages of units having higher values of m .

Typically the composition contains microbiologically produced PHA to the extent of over 50, especially over

80, % w/w.

The PHA is preferably a fermentation product, especially of a microbiological process in which a microorganism lays down PHA during normal growth or is
5 caused to do so by cultivation in the absence of one or more nutrients necessary for cell multiplication. The microorganism may be wild or mutated or may have had the necessary genetic material introduced into it. Alternatively the necessary genetic material may be
10 harboured by a eukariote, to effect the microbiological process.

Examples of suitable microbiological processes are the following:
for Formula I material with $m = 3$ or $m =$ partly 3, partly
15 4 : EP-A-69497 (Alcaligenes eutrophus);
for Formula I material with $m = 3$: US 4101533 (A. eutrophus H-16), EP-A-144017 (A. latus);
for Formula I material with $m = 7-13$: EP-A-0392687
(various Pseudomonas sp.).

20 The PHA can be extracted from the fermentation product cells by means of an organic solvent, or the cellular protein material may be decomposed leaving small granules of polymer for example of which less than 10% have diameters greater than 1 micrometres. For
25 specialised end uses the cellular protein may be partly or wholly allowed to remain with the PHA, but preferably subjected to cell breakage.

Alternately, the PHB or PHBV can be a product of synthetic chemistry (Bloembergen and Holden,
30 Macromolecules 1989, 22, p1656-1663. Bloembergen, Holden, Bluhm, Hamer and Marchessault, Macromolecules

1989, 22, p1663-1669).

The PHA may contain one or more nucleants, for example, boron nitride.

The PHA may optionally contain a variety of additives making it suitable for a range of applications. Such additives include tackifiers, waxes, plasticisers, stabilizers or antioxidants and compatible thermoplastic polymers. It is an advantage of the invention that good results can be obtained in the absence of tackifier.

The adhesive composition preferably contains 20 to 99% by weight of PHB or the copolymer PHBV, particularly 50 to 95%, especially 50 to 90%.

If a tackifier is present, the composition preferably contains 5 to 80% w/w thereof. Examples of suitable tackifiers include rosin and rosin derivatives, terpene phenolics and pure phenolic resins; and more specifically, gum rosin, wood rosin, tall oil rosin, distilled rosin, hydrogenated rosin, dimerized rosin, polymerised rosin, glycerol-, or pentaerythritol- esters of natural and modified rosins, such as for example wood rosin, the glycerol- or pentaerythritol- ester of hydrogenated rosin, the phenolic-modified pentaerythritol ester of rosin, phenolic modified terpene resins and hydrogenated derivatives thereof, and thermoplastic alkyl phenolic resins such as those described in USP 4,073,776 and USP 4,023,826.

A combination of two or more of the above mentioned tackifiers may be used if suitable.

If a wax diluent is present, the composition preferably comprises 1 to 30% w/w thereof. Suitable examples are 12-hydroxystearamide wax, hydrogenated

castor oil, oxidized synthetic waxes and polyethylene oxide.

If a stabilizer is present the composition preferably contains 0.1-4% w/w thereof. Suitable examples are high molecular weight phenols and multifunctional phenols such as sulphur and phosphorus-containing phenols, for example, 1,3,5-trimethyl-2,4,6-tris-(3,5-di-tert-butyl-4-hydroxy-benzyl)benzene; pentaerythritol tetrakis-3-(3,5-di-tert-butyl-4-hydroxyphenyl)-propionate; n-octadecyl-3,5-di-tert-butyl-4-hydroxyphenyl)-propionate; 4,4'-methylenebis (2,6-tert-butylphenol); 4,4'-thiobis (6-tert-butyl-o-cresol); 2,6-di-tert-butylphenol; 6-(4-hydroxyphenoxy)-2,4-bis(n-octyl-thio)-1,3,5-triazine; di-n-octadecyl-3,5-di-tert-butyl-4-hydroxybenzylphosphonate; 2-(n-octyl-thio)-ethyl-3,5-di-tert-butyl-4-hydroxy-benzoate; and sorbitol hexa[3-(3,5-di-tert-butyl-4-hydroxyphenyl)-propionate].

If a plasticiser is present, the ratio thereof to PHA may be up to 40 phr w/w and the range 5-20 especially 6-12, phr w/w is generally suitable.

Examples of suitable plasticisers are high-boiling esters of polybasic acids, such as phthalates, isophthalates, citrates, fumarates, glutarates, phosphates or phosphites. The esterified radicals may be for example C₁ - C₁₂ alkyl, aryl, aralkyl or aralkyl. Particular examples are dialkyl, for example dioctyl, phthalates, and dialkylalkylene oxide glutarates high-boiling esters and partial esters of polyhydric alcohols, especially glycols, polyglycols and glycerol. The acid-derived radical of the ester typically contains 2-10 carbon atoms. Examples are triacetin, diacetin and

glycerol dibenzoate and aromatic sulphonamides such as paratoluenesulphonamide

Particular examples of such plasticisers are esters of polyhydric alcohols, for example glyceryl esters of C₁ - C₄ carboxylic acids, especially Estaflex (Tradename).
5 Generally it is preferred that the plasticiser should be biodegradable.

Additional optional additives include colorants such as titanium dioxide, and fillers such as talc and clay.
10 These may be present in small amounts usually 0-20%, preferably 5 to 20%.

Particularly preferred PHA adhesive compositions comprise 50-95% PHA, 0-20% of plasticiser, 0-1% of nucleant, 0-20% of tackifier, 0-4% of stabiliser or
15 antioxidant, 0-10% of wax diluent, and 0-20% of a colorant and/or filler.

PHA adhesive formulations can be, for example, granules, dry powder or preferably latex suspensions. In such formulations the PHA is in particulate form before
20 the setting treatment. The adhesive layer may be at least partly discontinuous after the setting treatment. Granules may be formed by a normal extrusion process, using for example, a single or twin screw extruder in which the PHA powder is melted and passed through a die
25 before cutting into granules.

Amorphous PHA tends to crystallise with time and it may be supplied as an aqueous suspension or latex, in which the average particle size is from 0.1 µm to 2.0 µm and preferably from 1.0 µm to 2.0 µm.

30 Suitable latices can be produced in known processes for producing PHA, particularly polymers of

hydroxybutyric acid and copolymers thereof with hydroxyvaleric acid, in which microorganisms are grown under conditions such that they accumulate PHA and are then treated to break their cellular structure and to
5 release particles of PHA into an aqueous suspension. This can be accomplished for example by heat treatment and/or digestion with enzymes. Organic matter other than PHA is preferably largely removed, for example by separating the PHA from the liquid, preferably in the
10 presence of a surfactant.

The PHA may be resuspended in water to provide a suitable latex for use as an adhesive. Suitable latices and methods of their production are described in European Patent 145,233. Those containing peptidoglycan as the
15 major non-PHA cell material may be used. The peptidoglycan is believed to be present as a layer surrounding the substantially amorphous PHA particles. It need not be completely removed as it tends to isolate the particles from surrounding materials which may induce
20 crystallisation. The latex may be stabilised with a surfactant.

The process of the present invention may be carried out without heating if a latex is used. If powder or granules are used heating is usually necessary. The
25 adhesive composition is placed between the two articles in the cold state, preferably at a temperature from 15°C to 50°C, especially 15°C to 35°C. Then the articles are subjected to pressure and optionally a heat treatment to set the adhesive. Typically the pressure is applied in
30 the range 500 to 2000 and up to 10000 psig (34.5 to 690 bar), especially 500 to 8000 psig (34.5 to 550 bar) for

setting at the "cold" temperatures mentioned above.
Typically the heat treatment if used is in the range 120
to 190, especially 130 to 190, °C. pressures up to 2000
psig (138 bar) are then usually sufficient.

5 The adhesives of the present invention are useful
for a wide range of applications. Of particular interest
are sealing operations for example, in packaging and
carton sealing, in sanitary napkins, disposable baby
napkins and hospital equipment, etc. The adhesives are
10 useful for disposable articles in which at least one
flexible film material is bonded to at least one tissue,
non-woven, polyolefin or other flexible polymeric film
substrate. Alternately, the adhesive may bond elastic to
polyethylene, polypropylene or a non-woven substrate.

15 The adhesive composition when set does not
necessarily have to provide a permanent or strong bond in
order to satisfy the requirements of a particular bonded
article. In some cases it may be advantageous for the
bond to be weak enough to enable the articles to be
20 peeled apart. The adhesive layer contains PHA typically
at 0.1 to 10.0 g/dm².

Latex suspensions may be used in the absence of
nucleants, tackifiers, stabilisers, antioxidants,
plasticisers, colorants and fillers if desired.

25 The following examples illustrate the invention but
do not in anyway limit the scope of the invention.

Latex suspension preparation

A sample of fermentation broth from a culture producing
PHBV (11%mol HV) was heat shocked to break open the cells
30 and treated with a proteolytic enzyme followed by a water
wash regime as described in EP-A-145 233. At this stage

in the preparation a sample of latex suspension was taken for use in the present invention. The molecular weight of the PHBV in the latex suspension was 527,000.

Granule preparation

- 5 PHBV dry powder (24%mol HV) prepared by methods known in the art (available from ZENECA Bioproducts, PO Box 2, Belasis Avenue, Billingham, Cleveland, TS23 1YN, UK) was used to prepare PHBV granules (24%mol HV) containing 10 phr triacetin and 1 phr boron nitride. The granules were prepared by extrusion at a die temperature of 155°C (maximum). The molecular weight of the PHBV in the granules was 294,500.

Materials Specification

- Paper = 76.02 g/m²
15 Aluminium Foil = 33.81 g/m²
PHB-Film = 72.94 g/m²
Card = 340 to 550 g/m²

Sample preparation

Latex suspension adhesive (no heat treatment)

- 20 Strips (10cm x 2cm) of a range of materials were cut. Latex solution (40% w/w of PHA; 1ml) was pipetted on to the first test material. A second test material was overlaid on the first with a 5 cm overlap and then the combined test sample was put between two pieces of
25 MELINEX (trade mark) film and placed between two plates in a press at room temperature (20°C). The plates were adjusted until they touched the test sample and then pressure was applied to 5 tonnes (490 bar) and held for 1 minute. The pressure was released and the sample removed
30 from the plates. The samples were cut into 2 cm wide strips.

Latex suspension adhesive - (heat treatment)

Strips of a range of materials to be tested were cut into 20cm x 9 cm strips. Latex suspension (1ml) was pipetted on to an area in the centre of the first strip of test material with a 5 cm overlap. The second strip of test material was overlaid on top of the first strip of test material. Then the combined test sample was put between two pieces of "MELINEX" (trade mark) film and placed between two plates in a press. The press temperature was set to either 190°C or 134°C. Pressure was applied to 5 tonnes (109 bar) and held for 1 minute. The sample was removed quickly and allowed to cool. When completely cold the samples were cut into 2cm wide strips.

Granule adhesive - (heat treatment)

Strips (20cm x 9cm) of the materials to be tested were cut. One piece of test material was laid on a press with "MELINEX" (trade mark) film between it and the plate. Between 1.5g and 1.8g of granules were placed in the intended 5 cm overlap area and the second test material was laid on top of the first test material. "MELINEX" (trade mark) film was placed between the second test material and the second plate. The plates with the test sample between were transferred to a press at 190°C or 134°C. The pressure was increased to 5 tonnes (109 bar) and held for 1 minute at 190°C or 45 seconds at 134°C. The sample was then removed from the press and cooled. When completely cool the samples were cut into 2cm wide strips.

Peel test for adhesive strength

All the samples were tested for the strength of the adhesive bond using an Instron 1122C mechanical test

machine at a 90 degree peel angle, speed 10 mm per minute and at a temperature of 23°C. The bond strength is presented according to the following scale:

		Gic (Nm ⁻²)
5	VERY POOR	less than 1
	POOR	between 1 and 10
	LOW	between 10 and 100
	GOOD	between 100 and 500
	VERY GOOD	over 500

10 in which Gic (Nm⁻²) is (force ÷ width) x (1-cos Q) where Q is the peel angle. The results are presented in Table 1.

TABLE 1

	SPECIMEN		ADHESIVE TYPE	TEMP °C	BOND STRENGTH
	BASE	TOP			
15	PAPER	PAPER	LATEX	20	LOW
	PAPER	PAPER	LATEX	190	GOOD
	PAPER	Al-FOIL	LATEX	20	POOR
	PAPER	Al-FOIL	LATEX	190	POOR
	PAPER	PHB-FILM	LATEX	134	GOOD
20	CARD	PAPER	LATEX	20	POOR
	CARD	PAPER	LATEX	190	GOOD
	Al-FOIL	Al-FOIL	LATEX	190	LOW
	PHB-FILM	PHB-FILM	LATEX	20	POOR
	PHB-FILM	PHB-FILM	LATEX	134	V GOOD
25	CARD	PHB-FILM	LATEX	20	POOR

5

10

15

CARD	PHB-FILM	LATEX	134	GOOD
CARD	CARD	LATEX	20	V POOR
CARD	CARD	LATEX	190	GOOD
PAPER	PAPER	GRANULE	190	GOOD
PAPER	PAPER	GRANULE	134	GOOD
PAPER	Al-FOIL	GRANULE	134	POOR
PAPER	PHB-FILM	GRANULE	134	GOOD
CARD	PAPER	GRANULE	134	GOOD
Al-FOIL	Al-FOIL	GRANULE	190	POOR
Al-FOIL	Al-FOIL	GRANULE	134	POOR
Al-FOIL	PHB-FILM	GRANULE	134	POOR
CARD	Al-FOIL	GRANULE	134	POOR
CARD	PHB-FILM	GRANULE	134	GOOD
CARD	CARD	GRANULE	190	GOOD
CARD	CARD	GRANULE	134	GOOD

CLAIMS

- 1 Bonded articles in which the bond comprises a polyhydroxyalkanoate.
- 2 A process of bonding two or more articles together using an adhesive composition comprising at least one polyhydroxyalkanoate (PHA) wherein the PHA is placed between the articles to be bonded and the articles are subjected to pressure to set the adhesive, optionally at elevated temperature.
- 3 A process as claimed in Claim 2 in which the PHA is a polymer or copolymer of hydroxybutyric acid.
- 4 A process as claimed in Claim 2 or 3 in which the PHA is a copolymer of hydroxybutyric acid and hydroxyvaleric acid.
- 5 A process as claimed in Claim 4 in which the content of hydroxyvaleric units in the copolymer is in the range 10 to 28 mol percent.
- 6 A process as claimed in any one of Claims 2 to 5 in which the PHA is derived from a microorganism.
- 7 A process as claimed in any one of Claims 2 to 6 in which the PHA is applied to one or more of the articles as a latex of particles of PHA in water.
- 8 A process as claimed in Claim 7 which is carried out without heating and the pressure is in the range 34.5% to 690 bar.
- 9 A process as claimed in any one of Claims 2 to 6 in which the PHA is applied to one or more of the articles as a solid and the adhesive is subsequently set at an elevated temperature.
- 10 A process as claimed in any one of Claims 2 to 9 in which a nucleant, tackifier, plasticiser,

antioxidant, stabiliser, colorant or filler is present.

- 11 A process as claimed in any one of Claims 2 to 10 in which a PHA which is capable of attaining a high level of crystallinity is applied to one or more of the articles in a condition of low crystallinity and is set by increasing its crystallinity.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/GB 94/01496

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 C09J167/04

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 C09J

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US,A,5 169 889 (KAUFFMAN ET AL.) 8 December 1992 see the whole document -----	1-6,9-11



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents :

- 'A' document defining the general state of the art which is not considered to be of particular relevance
- 'E' earlier document but published on or after the international filing date
- 'L' document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- 'O' document referring to an oral disclosure, use, exhibition or other means
- 'P' document published prior to the international filing date but later than the priority date claimed

'T' later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

'X' document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

'Y' document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

'&' document member of the same patent family

Date of the actual completion of the international search

21 October 1994

Date of mailing of the international search report

- 9. 11. 94

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+ 31-70) 340-3016

Authorized officer

Decocker, L

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/GB 94/01496

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US-A-5169889	08-12-92	AU-B- 643154	04-11-93
		AU-A- 2134492	29-07-93
		CA-A- 2079535	28-07-93
		EP-A- 0553394	04-08-93
		JP-A- 5271638	19-10-93
		JP-B- 6062928	17-08-94
